



TECHNICAL BULLETIN

Raybo Chemical Company

TELEPHONE: 304-525-5171

RAYBO 64 — AquaSilk

Floating and Silking Control

REFERENCE	FEATURES	SYSTEM	COMMENTS	USAGE (%)	REFERENCE
	Floating and Silking Control	Water and Water Reducible Systems	Highly Effective	0.05-0.2% of Total Weight	

PERFORMANCE

RAYBO 64 is a balanced combination of primarily volatile compounds effective in controlling silking and floating. It is also useful in the control of "fisheyes", craters and orange peeling. RAYBO 64 leaves the film during the drying process ensuring the absence of solids which might have deleterious effects on coating properties. It is particularly useful in coating formulations containing small amounts of organic pigments in combination with large amounts of inorganic pigments such as TiO₂.

RAYBO 64 is an effective fluidizer producing better atomization and subsequent orange peel control in high polymers. RAYBO 64 is also effective in eliminating flooding.

The use of RAYBO 64 produces immediate results which will remain stable during storage. It can be used in water reducible and water systems.

ADVANTAGES

- Highly effective
- Produces immediate results
- Effective in both water and water reducible systems
- Solids listed with USDA

RECOMMENDATIONS

0.05-0.2% of Total Weight
 Post addition is recommended except in the case of flooding control where grind phase addition is recommended.
 RAYBO 64 may not perform well in certain latex systems.

PHYSICAL DATA**

Weight/Gallon 7.0 lbs.
 Viscosity 14.2 sec. #2 Zahn cup
 Appearance Lt. Blue Liquid

CONTAINER SIZES

North American: 5 gal. pail*, 55 gal. drum, and bulk.
 Global Zones: 5 gal. pail*, 55 gal. drum.

* One gallon containers available upon request.

** Typical Properties; not sales specifications.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

 Performance Additives
 Department
 Huntington, WV 25721
 Tel.: 304-525-5171
 Fax: 304-525-2921

U.S. Marketing Division
 Raybo Chemical Company
 Huntington, WV 25721
 Tel.: 304-525-5172
 Fax: 304-525-2921

 Exclusive Export
 Management Company
 W. R. Mangus, Inc.
 Tel.: 312-263-6124
 Email: rwmagnus@cocexport.com



Global Dist. Zones:
 Representatives in
 31 Countries